

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
28 October 2004 (28.10.2004)

PCT

(10) International Publication Number
WO 2004/092141 A1

(51) International Patent Classification⁷: C07D 233/54, C08G 59/68

(21) International Application Number:
PCT/EP2004/050501

(22) International Filing Date: 13 April 2004 (13.04.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0696/03 16 April 2003 (16.04.2003) CH

(71) Applicant (for all designated States except US): HUNTS-
MAN ADVANCED MATERIALS (SWITZERLAND)
GMBH [CH/CH]; Klybeckstrasse 200, CH-4057 Basel
(CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): WEIDMANN, Ulrich
[DE/CH]; Habsburgerstrasse 38, CH-4055 Basel (CH).

(74) Agent: MAUÉ, Paul Georg; Solvias AG, Patents, WKL-
402.3.041, Klybeckstrasse 191, CH-4002 Basel (CH).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.


(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:


— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: 1-IMIDAZOLYMETHYL-SUBSTITUTED-2-NAPHTOLS AND THEIR USE AS ACCELERATORS FOR LOW-TEMPERATURE CURING



(I)



(II)

(57) Abstract: Compounds of the general formulae (I) and (II): where R₁, R₂ and R₃ each independently of one another are H; C₁₋₁₇alkyl; C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups; C₄₋₂₀cycloalkyl-alkyl, optionally substituted by C₁₋₄alkyl groups; C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups. -CN, Hal, OH, or

C₁₋₁₀alkoxy; C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups; C₃₋₁₂alkenyl; C₃₋₁₂alkynyl; or aromatic or aliphatic C₃₋₁₂acyl; R₄, R₅, R₆, R₇, R₈, and R₉ each independently of one another are H; C₁₋₁₇alkyl; C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups; C₄₋₂₀cycloalkyl-alkyl, optionally substituted by C₁₋₄alkyl groups; C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups; C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups; C₃₋₁₇alkenyl; C₃₋₁₂alkynyl; C₁₋₁₂alkoxy; or OH; for formula (I) R is C₁₋₁₂alkyl; C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups; C₄₋₂₀cycloalkylalkyl, optionally substituted by C₁₋₄alkyl groups; C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups; C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups; C₃₋₁₂alkenyl; or C₃₋₁₂alkynyl; and for formula (II) n = 2 - 12; as accelerators in curable epoxy resin compositions which are used as a compression moulding compound, sinter powder, encapsulating system, or casting resin, or for producing prepreps and laminates having very good interlaminar shear strength values using the resin infusion method, wet layup method and injection methods, for producing components, especially components of large surface area.

JC20 Rec'd PCT/PTO 13 OCT 2005

1-IMIDAZOLYLMETHYL-SUBSTITUTED-2-NAPHTOLS AND THEIR USE AS ACCELERATORS FOR LOW-TEMPERATURE CURING

Accelerators for low-temperature curing

The invention relates to novel Mannich bases based on 1-imidazolylmethyl-substituted 2-naphthol compounds and also to their use as accelerators for epoxy resin systems which allow high ILS values in laminates, particularly for impregnation by resin infusion methods, the wet layup method and other impregnating methods. The accelerators of the invention are additionally suitable for sinter powder, casting resin and compression moulding compound applications.

The compound 1-imidazolylmethyl-2-naphthol and other imidazole catalysts and accelerators in connection with epoxy resins are known.

The customarily used imidazoles such as imidazole, 1-methylimidazole, 2-methylimidazole, 2-ethyl-4-methylimidazole or else 2-phenylimidazoles, however, in many epoxy resin formulations produce inadequate storage stabilities of preregs at room temperature when they are employed in prepreg formulations.

In the past attempts have been made to solve this problem by looking to reduce the reactivity of the imidazoles by formation of salts with organic or inorganic acids: see US 3,356,645 and US 5,001,212, for example. Although improvements in the storage stabilities of preregs (standing times for short) were achieved in those cases, they are still not sufficient for many applications.

Another way of improving the standing times of preregs is to form imidazole complexes by reacting imidazoles with metal salts: see US 4,101,514 and US 4,487,914, for example. Generally speaking, the improvement in the standing times that can be achieved in this way is obtained at the expense of an increase in the processing temperatures. Moreover, the metal complexes present in the cured epoxy resin system lead to a deterioration in the dielectric values and also to an increase in the water absorption. In many applications, however, it is required that there is no substantial change in water absorption, since otherwise the glass transition temperature may be lowered, which can lead to a considerable change in the mechanical, electrical and thermal properties of the impregnated component.

EP 0 761 709 describes 1-imidazolylmethyl-substituted 2-naphthol compounds as catalysts which make it possible substantially to avoid the disadvantages described in the above citations. The compounds in question are stable Mannich bases which in epoxy resin systems

- 2 -

lead to a markedly improved standing time of the overall system at room temperature. A formulation comprising such a catalyst can be cured rapidly in the temperature range between 110°C and 150°C. Materials of this kind exhibit good mechanical properties with relatively high glass transition ranges. Prepregs comprising such catalysts can be stored without problems for up to 16 days at room temperature and processed to laminates.

Established methods for producing favourably priced components of large surface area include resin infusion methods and other impregnating methods. In order to be able to be used in resin infusion methods, such as RTM, the epoxy resin formulation for use ought to have a viscosity of between 100 and 1000 mPa·s, but preferably from 100 mPa·s to 500 mPa·s, at a temperature of from 23°C to 60°C. For reasons of cost, the aim is for temperatures below 100°C during the impregnating operation. When, for example, the wet layup method is chosen for components of large surface area, the curing temperatures ought to remain well below 100°C, again on economic grounds. For reasons of greater ease of handling the semi-finished products manufactured in this way (prepregs) ought to have a relatively long storage stability at room temperature, which means that the prepreg must be capable of troublefree conversion to the laminate after storage for, for example, four days or more. Where laminates produced in this way are employed in energy-producing installations, the laminates being subject to rotational movements and considerable shear forces during their use, a certain minimum of adhesion is necessary between the individual layers which make up the laminate. One measure of this adhesion is that known as interlaminar shear strength, also called ILS for short, which is determined in accordance with the ASTM standard (ASTM D 2344-84). A maximum ILS value is therefore an aim for such applications.


It has now been found that 1-(imidazolyl)-2-methyl-2-naphthol does enable outstanding storage stabilities at room temperature in prepreg formulations but not very high interlaminar shear strength values. The maximum achievable value is approximately 22 MPa, irrespective of whether curing is carried out at 60°C for four hours, at 75°C for four hours or even eight hours or at 140°C for 30 minutes.

It has now surprisingly been found that Mannich bases based on 1-imidazolylmethyl-substituted 2-naphthol compounds, whose free aromatic hydroxyl group is alkylated, have a profile of properties which allows their advantageous use as accelerators for epoxy resin systems particularly for the resin infusion method, the wet layup method and impregnating methods, since semi-finished articles impregnated in this way, in addition to a prepreg

- 3 -

storage stability of 2-8 days, also give ILS values of up to 50 MPa when cured at 60°C or 75°C for from four to eight hours.

The present invention accordingly first provides compounds of the general formulae (I) and (II):



where

R₁, R₂ and R₃ each independently of one another are H; C₁₋₁₇alkyl;

C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups;

C₄₋₂₀cycloalkyl-alkyl, optionally substituted by C₁₋₄alkyl groups;

C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups, -CN, Hal, OH, or C₁₋₁₀alkoxy;

C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups;

C₃₋₁₂alkenyl; C₃₋₁₂alkynyl; or

aromatic or aliphatic C₃₋₁₇acyl;

R₄, R₅, R₆, R₇, R₈, and R₉ each independently of one another are H; C₁₋₁₇alkyl;

C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups;

C₄₋₂₀cycloalkyl-alkyl, optionally substituted by C₁₋₄alkyl groups;

C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups;

C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups;

C₃₋₁₇alkenyl; C₃₋₁₂alkynyl; C₁₋₁₂alkoxy; or OH; for formula (I)

R is C₁₋₁₂alkyl; C₃₋₁₂cycloalkyl, optionally substituted by C₁₋₄alkyl groups;

C₄₋₂₀cycloalkyl-alkyl, optionally substituted by C₁₋₄alkyl groups;

C₆₋₁₀aryl, optionally substituted by 1-3 C₁₋₄alkyl groups;

C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups;

C₃₋₁₂alkenyl; or C₃₋₁₂alkynyl; and for formula (II) n = 2 - 12.

Preferred compounds of the general formulae (I) and (II) in respect of the radicals R₁, R₂ and R₃ are those where R₁, R₂ and R₃ are each independently of one another H;

- 4 -

C₁₋₁₂alkyl; phenyl; or C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups; particular preference is given to compounds where R₂ and R₃ are each H; and R₁ is C₁₋₁₂alkyl; phenyl; or C₇₋₁₅phenylalkyl, optionally substituted by 1-3 C₁₋₄alkyl groups.

Preferred compounds of the general formula (I) in respect of the radical R are those where R is C₁₋₁₂alkyl; or C₃₋₁₂alkenyl; and preferred compounds of the general formula (II) are those where the factor n = 6 - 12 in respect of the unsubstituted aliphatic -(CH₂)-(CH₂)_n-CH₂- bridge.

Preferred compounds of the general formulae (I) and (II) in respect of the radicals R₄ to R₉ are those for which the stated radicals are a hydrogen atom (H).

The stated preferences for compounds of the general formulae (I) and (II) in respect of the radicals R₁, R₂ and R₃; of the radicals R₄ to R₉; of the radical R for compounds of the general formula (I), and in respect of the factor n for compounds of the general formula (II) also apply in any desired combination.

Particular preference is given to compounds of the general formulae (I) and (II) in which the radicals R₂ to R₉ are a hydrogen atom, and the radical R₁ is C₁₋₄alkyl (methyl, ethyl, n,i-propyl, n,i,t-butyl), or phenyl, optionally substituted by 1-3 C₁₋₄alkyl groups, and R is C₃₋₁₂alkyl or C₃₋₁₂alkenyl, and for formula (II) n = 8, 10, or 12.

Special preference is given to compounds where R₁ = methyl, R₂₋₉ are each a hydrogen atom, R = n-butyl, n-nonyl, n-dodecyl, or allyl, and n = 8.

The compounds of the invention can be prepared by methods which are known per se. For this purpose, first of all a 1-imidazolylmethyl-substituted 2-naphthol is prepared as described, for example, in EP 0 761 709 A. The hydroxyl group of the naphthol is subsequently etherified by conventional means, preferably in an alkali medium. In the case of the compounds of the formula (II) ring systems which are identical in each case are bridged by an aliphatic, unsubstituted hydrocarbon chain.

As mentioned at the outset, the compounds of the invention are suitable as accelerators for curable epoxy resin systems.

- 5 -

The invention therefore further provides curable epoxy resin compositions comprising

- a) an epoxy resin whose epoxide content is from 0.1 to 11, preferably from 0.1 to 2.2, epoxide equivalents/kg,
- b) a compound of the formula (I) or (II),
- c) a curing agent for the epoxy resin, and optionally
- d) an additive customary in epoxy resin technology.

In principle all epoxy resins are suitable as component (a).

Suitable examples include diglycidyl or polyglycidyl ethers of cycloaliphatic polyols, such as 2,2-bis(4'-hydroxycyclohexyl)propane, diglycidyl or polyglycidyl ethers of polyhydric phenols, such as resorcinol, bis(4'-hydroxyphenyl)methane (bisphenol F), 2,2-bis(4'-hydroxyphenyl)propane (bisphenol A), 2,2-bis(4'-hydroxy-3',5'-dibromophenyl)propane, 1,1,2,2-tetrakis(4'-hydroxyphenyl)ethane, or condensation products of phenols with formaldehyde, such as phenol novolaks and cresol novolaks; additionally, di- or poly(β -methylglycidyl) ethers of the above-cited polyalcohols and polyphenols; polyglycidyl esters and poly(β -methylglycidyl) esters of polybasic carboxylic acids such as phthalic acid, terephthalic acid, tetrahydrophthalic and hexahydrophthalic acid; glycidyl derivatives of aminophenols, such as triglycidyl-p-aminophenol; N-glycidyl derivatives of amines, amides and heterocyclic nitrogen bases, such as N,N-diglycidylaniline, N,N-diglycidyltoluidine, N,N,N',N'-tetraglycidyl-bis(4-aminophenyl)methane, triglycidyl isocyanurate, N,N-diglycidyl-N,N'-ethyleneurea, N,N'-diglycidyl-5,5-dimethylhydantoin, N,N'-diglycidyl-5-isopropylhydantoin, N,N'-diglycidyl-5,5-dimethyl-6-isopropyl-5,6-dihydrouacil; polyfunctional epoxy resins, such as the 2,6-disubstituted 4-epoxypropylphenyl glycidyl ethers and adducts thereof that are described in EP-A 205 409 and EP-A 204659; bisphenols such substituted with in each case two glycidyloxy groups and 2,3-epoxypropyl groups, such as the 2,2-bis(3'-epoxypropyl-4'-epoxypropylphenyl)propane described in GB 828364; glycidyl derivatives of tetramethylol-substituted cyclohexanols, cyclohexanones, cyclopentanols and cyclopentanones, such as the compounds described in US 4,549,008; glycidyloxy-substituted benzophenones; and glycidyloxydiketones, such as the compounds described in US 4,649,181.

In general it is also possible to use mixtures of two or more epoxy resins as components in the formulations of the invention.

Suitable epoxy resins include preferably glycidyl ethers such as bisphenol A or F, glycidyl

- 6 -

esters, N-glycidyl and N,O-glycidyl derivatives of aromatic or heterocyclic compounds, and also cycloaliphatic glycidyl compounds. They preferably have a functionality of from 0.1 to 2.2 epoxide equivalents/kg.

As curing agents, or component (c), it is possible in principle to use all of the curing agents which are customary in epoxy resin chemistry, such as amines, dicyandiamide, cyanoguanidines, melamines, novolaks, including cresol-novolaks, polyols and anhydrides, for example.

Curing agents suitable in principle also include the dihydroxy aromatics such as the bisphenols or diphenols already mentioned. Besides diphenols it is also possible to use triphenols or polyphenols, such as 2,4,6-tris[2'-(p-hydroxyphenyl)-2'-propyl]benzene (from Mitsui Petrochemical), for example.

As curing agent it is preferred to use amines and polyamines, examples being those of the Jeffamine D and T type, and others. Examples that may be mentioned include o-, m-, and p-phenylenediamine; diaminotoluenes, such as 2,4-diaminotoluene, 1,4-diamino-2-methoxybenzene, 2,5-diaminoxylene, 1,3-diamino-4-chlorobenzene, 4,4'-diaminodiphenylmethane, 4,4'-diaminodiphenyl ether, 4,4'-diaminodiphenyl thioether, 4,4'-diaminodiphenyl sulfone, 2,2'-diaminobenzophenone, 1,8- or 1,5-diaminonaphthalene, 2,6-diaminopyridine, 1,4-piperazine, 2,4-diaminopyrimidine, 2,4-diamino-s-triazine, di-, tri-, tetra-, hexa-, hepta-, octa-, and decamethylenediamine, 3-methylheptamethylene-1,6-diamine, 3-methoxyhexamethylenediamine, 2,11-diaminododecane, 2,2,4- and 2,4,4-trimethylhexamethylenediamine, 1,2-bis(3-aminopropoxy)ethane, N,N'-dimethylethylenediamine, N,N'-dimethyl-1,6-diaminohexane and also the diamines of the formulae

$\text{H}_2\text{N}(\text{CH}_2)_3\text{O}(\text{CH}_2)_2\text{O}(\text{CH}_2)_3\text{NH}_2$ and $\text{H}_2\text{N}(\text{CH}_2)_3\text{S}(\text{CH}_2)_3\text{NH}_2$, 1,4-diaminocyclohexane, 1,4-bis(2-methyl-4-aminopentyl)benzene, 1,4-bis(aminomethyl)benzene.

Additionally suitable amines are carbocyclic-aromatic diamines, especially substituted dinuclear diamines, such as bis(3,5-diisopropyl-4-aminophenyl)methane, bis(2-chloro-3,5-diethyl-4-aminophenyl)methane, bis(3-ethyl-4-amino-5-sec-butylphenyl)methane, bis(2-chloro-3,5-diethyl-4-aminophenyl)methane and bis(3,5-diethyl-4-aminophenyl)methane, for example.

Additionally suitable are propane-1,3-diamine, m-xylenediamine, bis(4-aminocyclohexyl)propane, 3-aminomethyl-3,5,5-trimethylcyclohexylamine (isophoronediamine),

- 7 -

polyaminoamides, examples being those consisting of aliphatic polyamines and dimerized or trimerized fatty acids; polyphenols, such as resorcinol, hydroquinone, bisphenol A and phenol/aldehyde resins, and also polythiols such as "Thiokols" for example.

Preferred curing agents are diamines or polyamines, amino-terminated polyalkylene glycols (e.g. Jeffamines, amino-poly-THF) or polyaminoamides, especially dimers or copolymers of propylene glycol and ethylene glycol, amino-terminated polybutadienes with molecular weights in the range from about 150 to 5000, in particular from 200 to 600.

Particularly preferred curing agents are amino-terminated polyetherdiamines, especially short-chain polyoxyalkylenediamines with a small (less than 10, preferably less than 6) repetition factor in respect of the polyoxyalkylene units. As commercially available curing agents mention may be made of Jeffamine® D-230, a polyoxypropylenediamine containing on average 2.6 oxypropylene units.

As optional component d) it is possible to use additives customary in epoxy resin technology. By these are meant the customary auxiliaries and additives which are known to and used by the person skilled in the art in respect of the particular application. Examples include organic and inorganic fillers and pigments, release agents, and viscosity-influencing additives.

To prepare the curable compositions of the invention the accelerators of the invention are dissolved beforehand in the curing agent, at generally elevated temperatures: for example, when using a Jeffamine®, at about 80°C. Solutions of this kind can be cooled to 40°C and then mixed with the epoxy resin. These mixtures can then be used directly as an RTM or impregnating solution. Another possibility is to disperse the accelerators of the invention homogeneously in the epoxy resin beforehand, by means for example of suitable stirrers, such as an Ultra-Turrax or a triple roll mill.

The compounds of the invention are used advantageously at from 1 to 10 parts by weight, based on the overall formulation. It is particularly advantageous to use from 5 to 7 parts by weight. The curing agents are employed in the customary amounts, which are therefore to be calculated such that on average per epoxide group there are from 0.5 to 1.5, preferably from 0.8 to 1.2, functional groups of the curing agent. Auxiliaries and additives can be used in principle in wide quantity ranges, provided that this is possible without a significant increase in the viscosity of the desired compositions.

- 8 -

As already mentioned, the compounds of the invention lower the storage stabilities of prepregs when they are used, for example, in epoxy resin/amine formulations and the prepregs thus prepared are stored at room temperature. However, prepregs comprising inventive accelerators of this kind have the capacity to give an ILS value of up to 50 MPa. Accordingly the accelerators of the invention are particularly suitable for use in epoxy resin formulations which are employed as compression moulding compounds, sinter powders, encapsulating systems, casting resins and for producing prepregs and laminates by the resin infusion method, wet layup method and injection methods.

Experimental section

a) Preparation of the Mannich bases. General description of the etherification of a naphthol, using 1-imidazolylmethyl-2-naphthol as example. Alkaline variant in DMSO.

A sulphonating flask (300-400 ml) provided with reflux condenser, internal thermometer, dropping funnel and KPG stirrer is charged with dimethyl sulphoxide and then the chosen naphthol is added with stirring. This gives a beige suspension. KOH in powdered form is added to the stirred solution. The solution changes its colour from beige to green and clarifies over the course of about 15 minutes to form a deep-green solution which still contains a few solid fractions. The internal temperature within the flask is approximately 22°C. At this temperature the alkyl halogen or the alkyl dihalogen, respectively, is added dropwise. The mixture is warmed to 30°C over 15 minutes. Then the remaining haloalkyl or dihaloalkyl is added over a further nine minutes. The contents of the flask are heated initially to just over 50°C and then to about 70°C. The flask is stirred at this temperature for two-three hours. Thereafter the reaction solution is poured onto 150 g of ice. A beige-brown solid and a milky aqueous phase are obtained. The organic phase is separated from the aqueous phase and the latter is extracted by shaking five times with 50 ml of toluene each time. The combined organic phases are dried over anhydrous sodium sulphate. After overnight standing and the removal of the drying agent on a suction filter, the solvent is removed on a rotary evaporator. This crude product is taken up in 20 ml of isopropanol and heated under reflux to about 65°C. The product is frozen out of the solution using dry ice, and isopropanol is removed on a suction filter. Finally the solid is dried at about 40°C/0.3 mbar for about two hours. The amounts of the individual components used can be found in Table 1 below.

- 9 -

Table 1:

E ¹⁾	Comp. 1 ²⁾	Comp. 2 ²⁾	Comp. 3 ²⁾	Solv. ³⁾	Yld. ⁴⁾	M.p. ⁵⁾
1	11.91 (50)	10.56 (51)	3.08 (55)	100	80-86	83
2	35.73 (150)	18.91 (153)	9.24 (165)	300	37	93
3	35.73 (150)	38.13 (153)	9.24 (165)	300	91	81
4	35.73 (150)	14.16 (153)	9.24 (165)	300	85	91
5	28.59 (120)	18.0 (60)	7.08 (126)	300	48	158

¹⁾ E = experiment; ²⁾ Comp. = component, amount in g and mmol (), component 1 = 1-imidazolylmethyl-2-naphthol, component 2 for E1 = nonyl bromide, E2 = allyl bromide, E3 = dodecyl bromide, E4 = butyl chloride, E5 = 1,10-dibromododecane; component 3 = KOH

³⁾ Solv. = solvent in ml, solvent in above experiments is in each case dimethyl sulphoxide (DMSO);

⁴⁾ Yld. = yield in %; ⁵⁾ m.p = melting point (DSC) in °C. Further characterization of the products was by ¹H and ¹³C NMR (d₆-DMSO) and C,H,N,O analyses.

The compounds of the invention are advantageously added in from 1 to 10 parts, in particular from 5 to 7 parts, by weight to the desired formulation. See also Table 2 in this regard.

b) Use examples of the Mannich bases of the invention

The products from the above experimental section a) are dissolved at temperatures between 60°C and 80°C in the amine curing agent. This gives orange to dark brown clear solutions. After cooling to room temperature, this solution is admixed with the calculated amount of epoxy resin. For details see Table 2 below:

Table 2

Experiment	Comparison	E6	E7	E8	E9	E10
LY 556 ¹⁾	100	100	100	100	100	100
Jeffamine ²⁾	10	10	10	10	10	8
Accelerator ³⁾	10					
E1 ⁴⁾		7				
E2 ⁴⁾			5			
E3 ⁴⁾				5	5	3
DY 965 ⁵⁾				5	10	
Minimum viscosity at 60°C [mPa·s] ¹²⁾	800-1000	150	150	150	Ng ¹¹⁾	150
Preparation ⁶⁾	8	2-7	2	2	2	2
Prepreg ⁷⁾	12	12	?	12	12	12
Resin content ⁸⁾	40-42	40-42	40-42	40-42	40-42	40-42
Storage ⁹⁾	RT	RT	RT	RT	RT	RT
Interlaminar shear strength (ILS) after 30 min at 140°C:						
F _{max} [N] ¹⁰⁾	601+/-38	2067+/-52	2109+/-52	1201+/-33	989+/-62	1037+/-20
σ _{max} [MPa] ¹⁰⁾	22.6+/-1.4	50.9+/-1.2	52+/-0.7	44.2+/-1.5	38.2+/-2.5	34.6+/-0.7
Interlaminar shear strength (ILS) after 4 h at 75°C:						
F _{max} [N]	426+/-37	496+/-30	Ng	964+/-73	1074+/-35	1082+/-29
σ _{max} [MPa]	16.0+/-1.4	13.4+/-0.7	Ng	38.1+/-1.8	40.3+/-0.9	40.6+/-1.3
Interlaminar shear strength (ILS) after 8 h at 75°C:						
F _{max} [N]	400+/-33	1271+/-125	Ng	959+/-48	927+/-36	1182+/-102
σ _{max} [MPa]	16.0+/-1.3	43.0+/-4.0	Ng	38.6+/-1.7	37.7+/-1.3	45.4+/-3.3
Interlaminar shear strength (ILS) after 4 h at 60°C:						
F _{max} [N]	Nm ¹¹⁾	2132 +/-14	Ng	Ng	Ng	Ng
σ _{max} [MPa]	Nm ¹¹⁾	50 +/-0.4	Ng	Ng	Ng	Ng


- ¹⁾ Araldite LY 556 Bisphenol-A Harz (Vantico AG)
- ²⁾ Jeffamine Jeffamine D-230 (Huntsman)
- ³⁾ XU 3123 1-Imidazolylmethyl-2-naphthol (Vantico AG)
- ⁴⁾ E1/E2/E3 Experiments 1, 2 and 3 (see Table 1)
- ⁵⁾ DY 965 Flexibilizing agent DY 965 (Vantico AG)
- ⁶⁾ Preparation Preparation of the prepregs and laminates after number of days
- ⁷⁾ Prepreg Number of plies =12
- ⁸⁾ Resin content1 Resin content in per cent after compression of the laminates
- ⁹⁾ Storage At 20°C to 25°C = RT
- ¹⁰⁾ F_{max} Ultimate strength (breaking load) to ASTM D 2344
- σ_{max} Shear strength to ASTM D 2344
- ¹¹⁾ Nm, Ng Nm = not measurable, Ng = not measured
- ¹²⁾ Viscosity Determined using Rheometrix RD2 with a plate/plate setup

- 11 -

Surprising are the very good interlaminar shear strengths which can be obtained with the accelerators of the invention in the lower temperature range (60°C and 75°C/4-8 hours), see Table 2, Formulations E6, E7 and Comparison. The values found are substantially higher than in the case of the comparison system. The viscosity level of 150 mPa·s which can be achieved with the accelerators of the invention at 60°C is also well below that of the comparison system, of 800-1000 mPa·s at 60°C. This is a key further advantage of the accelerators of the invention with a view to their use in infusion methods, since low viscosities are required therein.

Claims

1. Compounds of the general formulae (I) and (II):



where

R_1 , R_2 and R_3 each independently of one another are H; C_{1-17} alkyl;

C_{3-12} cycloalkyl, optionally substituted by C_{1-4} alkyl groups;

C_{4-20} cycloalkyl-alkyl, optionally substituted by C_{1-4} alkyl groups;

C_{6-10} aryl, optionally substituted by 1-3 C_{1-4} alkyl groups, -CN, Hal, OH, or C_{1-10} alkoxy;

C_{7-15} phenylalkyl, optionally substituted by 1-3 C_{1-4} alkyl groups;

C_{3-12} alkenyl; C_{3-12} alkynyl; or aromatic or aliphatic C_{3-12} acyl;

R_4 , R_5 , R_6 , R_7 , R_8 , and R_9 each independently of one another are H; C_{1-17} alkyl;

C_{3-12} cycloalkyl, optionally substituted by C_{1-4} alkyl groups;

C_{4-20} cycloalkyl-alkyl, optionally substituted by C_{1-4} alkyl groups;

C_{6-10} aryl, optionally substituted by 1-3 C_{1-4} alkyl groups;

C_{7-15} phenylalkyl, optionally substituted by 1-3 C_{1-4} alkyl groups;

C_{3-17} alkenyl; C_{3-12} alkynyl; C_{1-12} alkoxy; or OH; for formula (I)

R is C_{1-12} alkyl; C_{3-12} cycloalkyl, optionally substituted by C_{1-4} alkyl groups;

C_{4-20} cycloalkyl-alkyl, optionally substituted by C_{1-4} alkyl groups;

C_{6-10} aryl, optionally substituted by 1-3 C_{1-4} alkyl groups;

C_{7-15} phenylalkyl, optionally substituted by 1-3 C_{1-4} alkyl groups;

C_{3-12} alkenyl; or C_{3-12} alkynyl; and for formula (II) $n = 2 - 12$.

2. Compounds according to Claim 1, where R_1 , R_2 and R_3 each independently of one another are H; C_{1-12} alkyl; phenyl; or C_{7-15} phenylalkyl, optionally substituted by 1-3 C_{1-4} alkyl groups.
3. Compounds according to Claim 2, where R_2 and R_3 are each H; and R_1 is C_{1-12} alkyl; phenyl; or C_{7-15} phenylalkyl, optionally substituted by 1-3 C_{1-4} alkyl groups.

- 13 -

4. Compounds according to one of Claims 1 to 3, where for formula (I) R is C₁₋₁₂alkyl; or is C₃₋₁₂alkenyl; and for formula (II) n = 6 - 12.
5. Compounds according to one of Claims 1 to 4, where the radicals R₄ to R₉ are a hydrogen atom.
6. Compounds according to Claim 1, where R₁ = methyl, R₂₋₉ are each a hydrogen atom, R = n-butyl, n-nonyl, n-dodecyl, or allyl, and n = 8.
7. Use of a compound according to Claim 1 as accelerator in epoxy resin compositions.
8. Curable composition comprising
 - a) an epoxy resin whose epoxide content is from 0.1 to 11 epoxide equivalents/kg,
 - b) from 1 to 10 parts by weight, based on the overall composition from the components a) to d), of a compound according to Claim 1,
 - c) a curing agent for the epoxide resin, calculated such that per epoxide group there are from 0.5 to 1.5 functional groups of the curing agent, and optionally
 - d) an additive customary in epoxy resin technology.
9. Composition according to Claim 8, characterized in that the curing agent is selected from the amine group.
10. Composition according to Claim 9, characterized in that the curing agent is a polyoxypropylenediamine.
11. Composition according to Claim 8, characterized in that the epoxy resin is a glycidyl ether, glycidyl ester, N-glycidyl or N,O-glycidyl derivative of an aromatic or heterocyclic compound, or a cycloaliphatic glycidyl compound.
12. Use of a curable composition according to Claim 8 as a compression moulding compound, sinter powder, encapsulating system, casting resin, for producing preregs and laminates using the resin infusion method, wet layup method and injection methods.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP2004/050501

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0761709	A	12-03-1997	US 5591811 A	07-01-1997
			BR 9603729 A	26-05-1998
			CA 2185207 A1	13-03-1997
			DE 69608054 D1	08-06-2000
			DE 69608054 T2	11-01-2001
			EP 0761709 A2	12-03-1997
			ES 2146378 T3	01-08-2000
			JP 9118741 A	06-05-1997
			TW 487721 B	21-05-2002

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2004/050501

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C07D233/54 C08G59/68

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 761 709 A (CIBA GEIGY AG) 12 March 1997 (1997-03-12) cited in the application the whole document	1,7,8

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

28 July 2004

Date of mailing of the international search report

04/08/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fanni, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/050501

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0761709	A	12-03-1997	US 5591811 A	07-01-1997
			BR 9603729 A	26-05-1998
			CA 2185207 A1	13-03-1997
			DE 69608054 D1	08-06-2000
			DE 69608054 T2	11-01-2001
			EP 0761709 A2	12-03-1997
			ES 2146378 T3	01-08-2000
			JP 9118741 A	06-05-1997
			TW 487721 B	21-05-2002